

PRODUCT TECHNICAL CHARACTERISTICS

GROUP	<i>BIa</i>
MODEL	<i>BES. EUNOIA</i>
SIZE	<i>60X120</i>
COLOR	

CRITERIA	NORME STANDARD	MINIMUM REQUIREMENTS	Bestile	
Dimension and superficial aspect	ISO 10545-2	Longitude	600	± 2mm
		Width	1200	± 2mm
		Thickness	9,1	± 2mm
Groups of absorption of water	ISO 10545-3	0.5 % ≤ E ≤ 3% IND. MAX. 3,3%	0,1%	
Breaking charge N Thickness ≥ 7.5 mm	ISO 10545-4		1800 - 2400 N	
Flexion resistance N/mm ²	ISO 10545-4		45 - 55 N/mm ²	
Abrasion resistance PEI Clase	ISO 10545-7		I	II
			III <input checked="" type="checkbox"/>	IV
Linear thermal expansion	ISO 10545-8		< 7 x 10 ⁻⁶ °C	
Thermal shock	ISO 10545-9		Perform	
Expansion by humidity	ISO 10545-10	(mm / m)	< 0,1 mm/m	
Frost Resistance	ISO 10545-12		Perform	
Resistance to Household chemicals and: a) Acids b) Alkalis c) Swimming Pool Salts	ISO 10545-13	Ammonium Chloride 100g/l Sodium Hypochlorite 20mg/l	GA GA	
		Hydrochloric Acid 3% Citric Acid 100g/l Potassium Hydroxide 30g/l	PERFORM PERFORM PERFORM	
Resistance to stains	ISO 10545-14	Green Rust on Light Oil Alcoholic Iodine Solution Olive Oil	5 5 5	

Date
Responsible
BESTILE, S.L.

 Ptda. Torreta, s/n. - Tel. 964/367320 - Fax 964/...
 12110 ALCORA (Castellón) España
 C.I.F. B-12331377

01/03/23

Chief Laboratory